

DESCRIPTION AND USES

Mira-Var PRO Conversion Varnish is recommended for use on wood substrates that require high build and exceptional resistance properties at an economical price. Just like regular **Mira-Var**, it is recommended for use on kitchen cabinets and office furniture as well as any application where a high build, heavy duty wood coating is required. It does not offer the same level of UV light and ambering resistance as regular **Mira-Var**, but it still provides excellent water resistance, mar resistance, chemical resistance, and passes the KCMA performance standard.

SPECIFICATIONS

SURFACE PREPARATION: All wood surfaces to be finished must be clean, dry and free of contaminants such as oil or wax. Maple and birch should be sanded with 180 grit sandpaper prior to finishing. Moisture content of wood should be 7-9%. Oil-based stains should be allowed to dry a minimum of 24 hours before application of topcoat. Previously finished surfaces should be cleaned and thoroughly sanded with 220 grit sandpaper to ensure adhesion.

MATERIAL PREPARATION: **Mira-Var High Build Conversion Varnish** is a 2 component system. Add 4 Fl. oz. **710X Catalyst** per gallon of **Mira-Var Conversion Varnish**.

APPLICATION: **Mira-Var Conversion Varnish** is designed for all types of spray application. Because of the acid catalyst, all parts of equipment in contact with wet catalyzed coating must be stainless steel or plastic. Please refer to the supplier of your equipment for specifications on your particular requirements. Total film build should not exceed 4 dry mils. Stir all products well before use.

CLEAN UP: Use **910 Lacquer Thinner** to clean dried product off equipment.

PRECAUTIONS

This product is intended for use by properly trained professionals in a controlled environment. Always pre-test the product or system on the substrate you will be using and under your line conditions to confirm application suitability and to avoid the need for costly refinishing.

COMPANION PRODUCTS

- 730 Series Products
- 720 Series Sealers and Primers
- 710X Catalyst

PRODUCT CODES

- 732C - Clear Satin**
- 734C - Clear Soft Gloss**

TECHNICAL DATA

VEHICLE TYPE: Coconut Alkyd

VOLUME SOLIDS: 32%

WEIGHT SOLIDS: 40%

DENSITY: 7.7 lbs/gal

VOC: 4.55 lbs/gal

REGULATORY VOC: 550 g/L

CATALYZATION: Use 4 Fl. Oz./gallon of 88100 Catalyst

POT LIFE: 16 hours

SEALER: Self-seal OR Catalyzed or non-catalyzed vinyl sealer

CLEAN UP SOLVENT: Lacquer Thinner

REDUCING SOLVENT: Xylene

COVERAGE: 484 square feet at 1 mil dry film thickness.

DRY TIME: Dry to the touch in 30 minutes, sand in 60 minutes, re-coat in 4 hours.

SHELF LIFE: 1 year shelf life when properly stored.

For complete safety information, refer to the SAFETY DATA SHEET for this product.

RepcoLite
Quality Paint Since 1946

RepcoLite Paints, Inc.
473 W. 17th St.
Holland, MI 49423
(616) 396-1275
www.repcolite.com